

Muon spin rotation and relaxation in the superconducting ferromagnet UCoGe

A. de Visser,^{1,*} N. T. Huy,^{1,†} A. Gasparini,¹ D. E. de Nijs,¹ D. Andreica,^{2,‡} C. Baines,² and A. Amato²

¹*Van der Waals - Zeeman Institute, University of Amsterdam,
Valckenierstraat 65, 1018 XE Amsterdam, The Netherlands*

²*Laboratory for Muon-Spin Spectroscopy, Paul Scherrer Institute, CH-5232 Villigen, Switzerland
(Dated: April 3, 2009)*

We report zero-field muon spin rotation and relaxation measurements on the superconducting ferromagnet UCoGe. Weak itinerant ferromagnetic order is detected by a spontaneous muon spin precession frequency below the Curie temperature $T_C = 3$ K. The μ^+ precession frequency persists below the bulk superconducting transition temperature $T_{sc} = 0.5$ K, where it measures a local magnetic field $B_{loc} = 0.015$ T. The amplitude of the μ SR signal provides unambiguous proof for ferromagnetism present in the whole sample volume. We conclude ferromagnetism coexists with superconductivity on the microscopic scale.

PACS numbers: 74.70.Tx, 75.30.Kz, 76.75.+i

Recently, it was shown [1] that UCoGe belongs to a new family of ferromagnetic metals which become superconducting at low temperatures. One of the most intriguing properties of these superconducting ferromagnets (SCFMs) is that both ordering phenomena coexist. Such a coexistence is incompatible with the standard BCS theory for superconductivity (SC), because the ferromagnetic (FM) exchange field prevents phonon-mediated formation of singlet Cooper pairs [2]. However, for weak itinerant ferromagnets, like UCoGe, an alternative route is offered by spin fluctuation models [3, 4], in which critical magnetic fluctuations near a magnetic phase transition can mediate unconventional SC by pairing electrons in a spin triplet state. Superconductivity not mediated by phonons [5] attracts a wide interest as it plays a central role in the quest to unravel high temperature SC in the cuprates [6] and the oxypnictides [7] discovered recently. The SCFMs discovered so far are UGe₂ (under pressure) [8], UIr (under pressure) [9], URhGe [10] and UCoGe. The coexistence of itinerant FM and SC in these compounds marks a clear distinction with other families of superconductors, like Chevrel phases [11] and borocarbides [12], in which local-moment (anti)ferromagnetism and SC exist, but expel each other. In the case of UGe₂ [13] and URhGe [14] experimental evidence is at hand that SC is driven by critical magnetic fluctuations near a magnetic transition between two polarized phases. In contrast, UCoGe may present the first example of SC stimulated by critical fluctuations associated with a FM quantum critical point.

FM order in UCoGe with a Curie temperature $T_C = 3$ K was first observed by magnetization $M(T, B)$ measurements on polycrystalline samples [1]. The small (polycrystalline averaged) ordered moment $m_0 = 0.03 \mu_B$ and the low coercive field of ~ 1 mT indicate magnetism is weak. The analysis of the magnetization by means of Arrott plots shows UCoGe is an itinerant FM. This is further corroborated by specific heat data, which show the entropy associated with the magnetic transition is small

(0.3 % of $R\ln 2$). Subsequent $M(T, B)$ data taken on single crystals reveal a strong uniaxial magnetic anisotropy: the moment $m_0 = 0.07 \mu_B$ points along the orthorhombic c axis [15]. In the FM state SC occurs with a resistive transition temperature $T_{sc} = 0.8$ K for the best polycrystalline samples. Measurements of the upper critical field B_{c2} provide evidence for unconventional SC, characterized by an equal-spin pairing triplet state and a SC gap function with point nodes along the direction of the uniaxial moment [15].

Although FM order is a robust property of our poly and single-crystalline samples, it has not been probed directly via magnetization below 1.8 K [1]. Moreover, the $M(T, B)$ data alone cannot exclude that the small moment is due to a reduced volume part of the sample exhibiting FM order with a larger magnetic moment. Evidence obtained so far for the coexistence of SC and FM stems mainly from macroscopic measurements, notably thermal expansion [1]. The sizes of the steps in the coefficient of linear thermal expansion at T_C and T_{sc} indicate magnetism and SC occur in the whole sample, however, again, reduced volume fractions cannot be ruled out. Therefore, it is of paramount importance to investigate the magnetic response of UCoGe on a microscopic scale. The μ SR technique is extremely suitable for this purpose [16]. Positive muons μ^+ , when implanted in the sample, act as a sensitive probe of the local field, which permits to discern magnetically inequivalent sample regions. In this Letter we present a μ SR study on UCoGe which provides unambiguous proof for magnetic order in the whole sample volume. FM coexists with SC below T_{sc} . Our work is the first μ SR study conducted on a SC itinerant FM below its SC transition temperature. The muon response in the SC state provides evidence for a spontaneous vortex phase in zero field. Furthermore, our results provide insight in the intricate problem of how the superconductor accommodates the FM structure.

A batch of polycrystalline UCoGe was prepared as described in Ref. [1]. Measurements of the electrical resis-

tivity, $R(T)$, show the residual resistance ratio $RRR = R(300 \text{ K})/R(1 \text{ K}) \approx 30$ and the FM and SC transitions occur at 3.0 K and 0.8 K (onset), respectively (see Fig. 3a). Zero-field (ZF) μ SR experiments were performed at the Paul Scherrer Institute in the General Purpose Spectrometer (GPS) using a ^4He flow cryostat in the temperature range $T = 1.6 - 10 \text{ K}$ and in the Low Temperature Facility (LTF) using a dilution refrigerator for $T = 0.02 - 5.5 \text{ K}$. Two identical μ SR samples were prepared. Each sample consisted of four thin slices (thickness 0.8 mm, area $6 \times 10 \text{ mm}^2$) that were cut from the annealed button by spark erosion. The surface layer, defected by spark erosion, was removed by polishing. The total sample area was $12 \times 20 \text{ mm}^2$ and matched the cross-sectional area of the muon beam in order to eliminate contributions from the sample holder. One sample was measured in the GPS and the other in the LTF. In addition we carried out ZF μ SR experiments on polycrystalline $\text{URh}_{0.4}\text{Co}_{0.6}\text{Ge}$, which has a Curie temperature $T_C = 20.0 \text{ K}$ [17] and a (polycrystalline averaged) ordered moment $m_0 = 0.22 \mu_B$ [18].

ZF μ SR is a well known technique to study magnetically ordered phases. Polarized muons are implanted into a sample where their spins $\mathbf{S}_\mu$ ($S_\mu = 1/2$) precess in the local magnetic field $\mathbf{B}_{loc}$ until they decay. $\mathbf{S}_\mu(t)$ is monitored through the decay positron. By measuring the asymmetric distribution of emitted positrons the time evolution of the polarization $\mathbf{P}_\mu(t)$ can be deduced. $P_\mu(t)$ is defined as the projection of $\mathbf{P}_\mu(t)$ along the direction of initial polarization $P_\mu(t) = \mathbf{P}_\mu(t) \cdot \mathbf{P}_\mu(0)/P_\mu(0) = G(t)P_\mu(0)$, where $G(t)$ reflects the normalized muon-spin autocorrelation function $G(t) = \langle \mathbf{S}_\mu(t) \cdot \mathbf{S}_\mu(0) \rangle / S_\mu(0)^2$. The muon depolarization function $G(t)$ extracted from the μ SR spectra contains the information on the averaged value, distribution and time evolution of the internal magnetic fields and is to be compared with selected theory functions.

A typical ZF μ SR spectrum on UCoGe in the paramagnetic state at $T = 5.5 \text{ K}$ is shown in Fig. 1a. This spectrum is best described by the standard Kubo-Toyabe function:

$$G_{KT}(t) = \frac{1}{3} + \frac{2}{3}(1 - \Delta_{KT}^2 t^2) \exp(-\frac{1}{2}\Delta_{KT}^2 t^2) \quad (1)$$

The Kubo-Toyabe function describes the muon depolarization due to an isotropic Gaussian distribution of static internal fields centered at zero field. $\Delta_{KT} = \gamma_\mu \sqrt{\langle B^2 \rangle}$ is the Kubo-Toyabe relaxation rate, with γ_μ the muon gyromagnetic ratio ($\gamma_\mu/2\pi = 135.5 \text{ MHz/T}$) and $\langle B^2 \rangle$ the second moment of the field distribution. Spectra taken in the paramagnetic phase show Δ_{KT} is $0.30 \pm 0.01 \mu\text{s}^{-1}$ and is independent of temperature. This indicates the depolarization is not due to electronic magnetic moments, but rather due to static nuclear moments of the ^{59}Co atoms ($\mu_{Co} = 5.23 \mu_N$, the spin $I = 7/2$ and the abundance is 100 %).




FIG. 1: Typical zero-field μ SR spectra in polycrystalline UCoGe: (a) in the paramagnetic phase at $T = 5.5 \text{ K}$ (solid line fit to Eq. 1), and (b) in the ferromagnetic phase at $T = 0.02 \text{ K}$, well below the superconducting transition temperature (solid line fit to Eq. 2).

In the FM state, a clear spontaneous μ^+ precession frequency ν is observed. A typical spectrum, taken at $T = 0.02 \text{ K}$ is shown in Fig. 1b. This response has an electronic origin and is best described by the depolarization function of an isotropic polycrystalline magnet with a Lorentzian field distribution:

$$G_M(t) = \frac{1}{3} \exp(-\lambda_1 t) + \frac{2}{3} \exp(-\lambda_2 t) \cos(2\pi\nu t + \phi) \quad (2)$$

The first term corresponds to an average of $1/3$ of the muons that sense a local field parallel to their initial polarization and therefore do not precess, where λ_1 is a measure for the internal spin dynamics perpendicular to the muon spin. The ‘ $2/3$ term’ probes the local field which results in a precession of the muon spin with frequency ν (ϕ is a phase factor) and λ_2 is a measure for both static and dynamical spin effects. By fitting the spectrum taken at $T = 0.02 \text{ K}$ (Fig. 1b) to Eq. 2 we obtain the spontaneous frequency $\nu = 1.972 \pm 0.004 \text{ MHz}$, and the damping rates $\lambda_1 = 0.152 \pm 0.006 \mu\text{s}^{-1}$ and $\lambda_2 = 2.372 \pm 0.004 \mu\text{s}^{-1}$. The measured value of λ_1 confirms the ‘ $1/3$ ’ term is due to the sample and muons do not stop in the sample holder. As will be demonstrated below, the spontaneous μ^+ precession frequency characterizes the weak itinerant FM order. The observed frequency corresponds to a local field $B_{loc} \sim 0.015 \text{ T}$ at the muon localization site.

In order to investigate the evolution of the magnetic volume fraction in the temperature regime of the FM transition we have fitted the μ SR spectra to a two-component depolarization function:

$$G(t) = A_{magn} G_M(t) + A_{para} G_{KT}(t) \quad (3)$$

Here A_{magn} and A_{para} represent the volume fractions




FIG. 2: Temperature variation of the normalized asymmetries of the ferromagnetic and paramagnetic phase in UCoGe. Below ~ 1.5 K magnetism is observed in the whole sample volume. The solid lines are to guide the eye.

of the ferro- and paramagnetic phases, respectively, with normalization $A_{magn} + A_{para} = 1$. In Fig. 2 we show the deduced temperature variation $A_{magn}(T)$ and $A_{para}(T)$. The magnetic transition is relatively broad in our polycrystalline samples. Below ~ 1.5 K $A_{magn}(T) \rightarrow 1$ and magnetism is present in the whole sample volume. The ZF asymmetry is within error bar equal to the asymmetry measured in transverse field (TF = 50 G) at temperatures of 5.5 K (LTF) and 10 K (GPS), which confirms the full signal amplitude is involved.

In Fig. 3 we show $\nu(T)$, which tracks the magnetization $M(T)$ [1]. The $\nu(T)$ data can be well fitted to the phenomenological order-parameter function $\nu(T) = \nu_0(1 - (T/T^*)^\alpha)^\beta$. The spontaneous frequency vanishes near $T^* = 3.02$ K $\approx T_C$ and $\nu_0 = 1.98$ MHz. Notice the critical exponent $\alpha = 2.3$ deviates from the standard value $3/2$ for spin waves, while $\beta = 0.4$ is larger than the theoretical value $5/16$ for a 3D Ising-like FM [19].

In order to further explore the μ SR spectra in the magnetic state we have carried out ZF muon spin rotation experiments on UCoGe doped with Rh. Upon substituting Rh for Co the Curie temperature and the ordered moment steadily increase and reach the values $T_C = 20.0$ K [17] and $m_0 = 0.22 \mu_B$ [18] for 40 at. % Rh. ZF μ SR spectra on polycrystalline URh_{0.4}Co_{0.6}Ge were collected in the GPS for $T = 5 - 25$ K. In the FM phase the muon depolarization is described by Eq. 2, but best fits were obtained with a Gaussian damping factor $\exp(-\frac{1}{2}\sigma_G^2 t^2)$ for the ‘ $2/3$ term’. From the amplitude of the signal we conclude magnetism is observed in the whole sample volume. The main feature of the spectra is the spontaneous μ^+ precession frequency below T_C , which attains a value of 14.1 MHz at the lowest temperature (see inset of Fig. 3). $\nu(T)$ follows an order-parameter variation with $T^* = 20.1$ K $\approx T_C$. The values $\alpha = 2.2$ and $\beta = 0.4$ are similar to the ones derived from the magnetization [18], and identical, within the error bars, to the values obtained for UCoGe. The precession fre-




FIG. 3: (a) Resistivity versus temperature of polycrystalline UCoGe. (b) Spontaneous muon precession frequency $\nu(T)$ of UCoGe and (lower inset) URh_{0.4}Co_{0.6}Ge. The solid lines represent fits to a phenomenological order parameter function (see text). Notice the 2% decrease of $\nu(T)$ below the bulk T_{sc} of 0.5 K [1]. Upper inset: $\lambda_2(T)$ of UCoGe.

quency $\nu(0)$ is a factor ~ 7 larger than the one of UCoGe and scales with the ratio of the ordered moments (~ 7) deduced from the dc-magnetization [18]. We conclude the analysis of the ZF μ SR spectra of URh_{0.4}Co_{0.6}Ge corroborates the results for UCoGe.

Next we discuss the possible muon localization site. UCoGe crystallizes in the orthorhombic TiNiSi type structure [20, 21] (space group $Pnma$), where the U, Co and Ge atoms occupy the 4c sites (Wyckoff notation). The most probable localization sites are the high symmetry interstitial 4a and 4b positions. By calculating Δ_{KT} due to the ^{59}Co nuclear moments ($T > T_C$) one can in principle determine the stopping site [22]. From a search along high symmetry directions in the crystal leads we tentatively assign the μ^+ localization site to the 4a position, where $\Delta_{KT} = 0.34 \mu\text{s}^{-1}$ [23], close to the experimental value of $0.30 \pm 0.01 \mu\text{s}^{-1}$. The local field in the FM phase (in ZF) is given by $B_{loc} = B_{dip} + B_c + B_L$, where B_{dip} is the dipolar sum of the ordered moments, B_c is the contact hyperfine field and $B_L = \mu_0 M_s / 3$ the Lorentz field with M_s the saturation magnetization (see for example Ref. [24]). For a precise determination of the different terms Knight shift experiments on a single crystal are required. However, dipolar calculations yield the following estimates: with $m_0 = 0.07 \mu_B \parallel c$ at the U atoms [15], we derive for the 4a site $B_{dip} = 0.015$ T, $B_L = 0.005$ T, and by comparing to the experimental value B_{loc} of 0.015 T, a negative contact field $B_c = -0.005$ T.

We now have a detailed understanding of the ZF muon

spin rotation data and proceed to make a number of important conclusions. First of all, the data provide unambiguous proof for ferromagnetism present in the whole sample volume. The spontaneous μ^+ precession signal persists with the same asymmetry below the SC transition temperature (see Fig. 3). Thus FM and SC coexist. Interestingly, in the SC state the precession frequency shows a small decrease of about 2 %. This decrease is measured by the whole muon ensemble. It provides a first indication of the interplay of magnetism and SC in UCoGe. The decrease of ν below T_{sc} is possibly due to induced screening currents that lead to a small reduction of the local field. On the other hand, the damping factor λ_2 slightly increases when passing through T_{sc} (see Fig.3). Such a broadening of the field distribution is expected when a spontaneous vortex phase [25] is formed. This indicates the local field is larger than the lower critical field B_{c1} and the sample is always in the mixed state. Our results also shed light on the intricate question of how the SC state accommodates FM order. The strong uniaxial magnetic anisotropy [15] excludes the formation of a modulated or spiral magnetic structure when passing through T_{sc} , like observed in ErRh_4B_4 [26]. This is corroborated by the minor changes in the μSR spectra below T_{sc} . It has been proposed that the SC transition should be accompanied by a redistribution of FM domains [27, 28], however, such a redistribution cannot be detected in our polycrystal data. μSR experiments on single-crystals are needed to elucidate these issues further.

We emphasize the FM state is observed in zero applied magnetic field. Recent magnetization measurements on single crystals ($RRR = 20$) led to the claim that a magnetic field of the order of a few mT is needed to stabilize FM order [29]. This is at variance with our results [15] and indicates metallurgy of UCoGe is an important issue. This might also be of relevance for understanding recent Co NMR and NQR data obtained on powdered samples [30]. The analysis reveals a two-component nuclear spin relaxation rate $1/T_1$, yielding evidence for an inhomogeneous sample and a SC volume fraction of 30 %.

In summary, we have used the μSR technique to investigate the weak itinerant FM phase in UCoGe. Below $T_C = 3$ K a spontaneous μ^+ precession frequency appears, which probes a local field B_{loc} of 0.015 T when $T \rightarrow 0$. Muons most likely localize at the 4a site, as deduced from calculations of the Kubo-Toyabe relaxation rate. The μ^+ precession frequency persists below T_{sc} , where FM and SC coexist on the microscopic scale.

This work was part of the research program of the Dutch Foundation FOM. Part of this work was carried out at the Swiss Muon Source $S\mu\text{S}$ (PSI, Villigen, Switzerland) with support of the European Commission under the 6th Framework Programme through the COST

Action P16 ECOM and the Key Action Strengthening the European Research Area, Research Infrastructures (contract RII3-CT-2003-505925).

* Electronic address: devisser@science.uva.nl

† Current address: Hanoi Advanced School of Science and Technology, Hanoi University of Technology, 1 Dai Co Viet, Hanoi, Vietnam

‡ Current address: Faculty of Physics, Babes-Bolyai University, 400084 Cluj-Napoca, Romania

- [1] N. T. Huy *et al.*, Phys. Rev. Lett. **99**, 67006 (2007).
- [2] N. F. Berk and J. R. Schrieffer, Phys. Rev. Lett. **17**, 433 (1966).
- [3] D. Fay and J. Appel, Phys. Rev. B **22**, 3173 (1980).
- [4] G.G. Lonzarich, in *Electron: A Centenary Volume*, ed. M. Springford (Cambridge Univ. Press, Cambridge, 1997), Chapter 6.
- [5] P. Monthoux, D. Pines, and G. G. Lonzarich, Nature (London) **450**, 1177 (2007).
- [6] J. G. Bednorz and K. A. Müller, Z. Physik B **64**, 189 (1986).
- [7] Y. Kamihara *et al.*, J. Am. Chem. Soc. **130**, 3296 (2008).
- [8] S. S. Saxena *et al.*, Nature (London) **406**, 587 (2000).
- [9] T. Akazawa *et al.*, J. Phys.: Condens. Matter **16**, L29 (2004).
- [10] D. Aoki *et al.*, Nature (London) **413**, 613 (2001).
- [11] Ø. Fischer, Appl. Phys. **16**, 1 (1978).
- [12] R. J. Cava *et al.*, Nature (London) **367**, 252 (1994).
- [13] C. Pfleiderer and A. D. Huxley, Phys. Rev. Lett. **89**, 147005 (2002).
- [14] F. Lévy *et al.*, Science **309**, 1343 (2005).
- [15] N. T. Huy *et al.*, Phys. Rev. Lett. **100**, 077002 (2008).
- [16] A. Amato, Rev. Mod. Phys. **69** 1119 (1997).
- [17] S. Sakarya *et al.*, J. Alloys Comp. **457** 51 (2008).
- [18] N. T. Huy, *Ph.D. Thesis* (University of Amsterdam, 2008); N. T. Huy and A. de Visser, e-print arXiv:0902.0974v1.
- [19] J. E. Essam and M. E. Fisher, J. Chem. Phys. **38**, 802 (1963).
- [20] B. Lloret, *Ph.D. Thesis* (University Bordeaux I, 1988).
- [21] F. Canepa *et al.*, J. Alloys Comp. **234**, 225 (1996).
- [22] A. Schenck, *Muon Spin Rotation Spectroscopy* (Adam Hilger, Bristol, 1985).
- [23] For the 4b site $\Delta_{KT} = 0.20 \mu\text{s}^{-1}$. The second moment calculation includes quadrupolar coupling effects. We assume a radial electric field gradient and neglect the small contribution from nuclear moments at Ge atoms.
- [24] A. Schenck and F. N. Gygas, *Handbook of Magnetic Materials* Vol. 9, ed. K.H.J. Buschow (North Holland, Amsterdam, 1995) Chapter 2.
- [25] M. Tachiki *et al.*, Solid State Comm. **34**, 19 (1980).
- [26] S. K. Sinha *et al.*, Phys. Rev. Lett. **48**, 950 (1982).
- [27] P. W. Anderson and H. Suhl, Phys. Rev. **116**, 898 (1959).
- [28] E. B. Sonin, Phys. Rev. B **66**, 100504(R) (2002).
- [29] J. Poltírová Vejprová, J. Pospíšil, and V. Sechovský, e-print: arXiv:0806.3561v1.
- [30] T. Ohta *et al.*, J. Phys. Soc. Jpn **77**, 023707 (2008).